

Trav. de las Corts, 371, 3° 1° 08029 BARCELONA (Spain) Telf.: (+34) 93 410 87 32 Fax.: (+34) 93 410 04 42 N.I.F/V.A.T N°: ES B64349236 www.krabchemical.com

Customer	Country	Technical	Date	Reference
Laboratory	España	Tino Fernandez	15-05-10	W.B
Article Wet-blue full tanning	X Tanning Re-Tanni		ing	
Origin		Made in	X Factory Laboratory	Material
Comments To obtain some looth are to mine when	a Alexandra made al legge die a	Shaving (mm.)	Pieces	Kgs.
To obtain some leathers tanning where veins of blood and some leathers more				

OPERATION	%	PRODUCTS	°C	TIME	PH	REMARK
	80	Pikel bath			3.2	
1:4	1	KRANOPOL UK		10′		
1:4	2.5	KRAPOL 40		10′		
	2	KRACROM 26/33		60′		#
To add	50	water	45°			
	4	KRACROM 26/33				
1:20	0.15	K-THIO BS 20		120′		
	0.5	Magnesium Oxide		8 hours	4	TC-2′-100°C
Draim – Wash						
	100	Water	25°			_
1:20	0.08	K-THIO BS 20		60′	·	
To discharge					·	

Pelt weight 3.8 mm - "Comparatives"

	NORMAL TANNING LOT	TANNING LOT with KRAPOL 40		
NECK WRINKLE	Normal	+ smooth		
FULL SKIN	Normal	+ full		
VEINS OF BLOOD	Very marked	Not so marked		
SQUARE FOOT W.B	Normal	+ 2% aprox.		
PORE FINENESS	Normal	+ fine		
CHROME IN FINAL BATH	3-4 mlgrs / Lt	0.8-1.0 mlgrs / Lt		
EXAMPLES				
122 PIECES	2.490 kgs - 5.372 sq ft	2.460 kgs - 5.488 sq ft		
150 PIECES	2.720 kgs - 5.810 sq ft	2.690 kgs - 5.898 sq ft		

REMARK IN LEATHER

Leathers more smooth and bigger square foot Less chrome used for tanning giving a quite exhausted bath

^{*} The content of this document is alone indicative. We don't take the responsibility of the inadequate use of our products *